



# THAIPRODUCTS FOAM COMPANY LIMITED

**Properties:** OSE: P572 I (Protective film)

<b>Tesile strength, MPa</b>	
Machine direction	14.1
Cross machine direction	22.0
<b>Elongation at break,%</b>	
Machine direction	4.92
Cross machine direction	7.57
<b>Stress at 300% elongation,MPa</b>	
Machine direction	829
Cross machine direction	683
<b>Tear strength,mN</b>	
Machine direction	16.4
Cross machine direction	31.0
<b>Specific gravity</b>	0.848

Tensile strength, Elongation and Stress at 300% elongation: ASTM D 882

Tear strength: ASTM D 1922

Specific gravity: ASTM D 792